

EPOMARINE AE-10 耐油导静电涂料

PRODUCT DESCRIPTION

产品简介

A two pack amine adducts cured epoxy paint with conducting electrostatic materials.

是一种添加导静电材料的双组份胺加成物固化型环氧涂料。

RECOMMENDED USE

用途

As long-term conducting electrostatic anti-corrosive coating on steel tank of interior surface for petroleum products. The surface resistivity is 10^8 - 10^{11} ohms.

作为长效导静电防腐涂料，使用于装载石油制品的钢制储罐内壁。表面电阻率为 10^8 - 10^{11} 欧姆。

COMPLIED STANDARDS

符合标准

Complies with GB/T 13348-2009

符合液体石油产品静电安全规程 GB/T 13348-2009

FEATURES

产品特性

Excellent corrosive resistance

极好的防腐性能

a long-term stable conducting electrostatic properties

长效的导静电性能

Excellent osmosis resistance

优异的抗渗透性

Non-pollution for petroleum products

对石油制品无污染

Light colors

浅色

PHYSICAL PROPERTIES

基本数据

Color

颜色

Grey and White

灰色和白色

Volume Solids

体积固体份

48%

VOC

挥发性有机化合物含量

460g/L, accord with EU Dirertive2004/42/EC, subcategory j

460 克/升，符合欧盟溶剂排放指令 2004/42/EC, j 子类别

Flash Point

闪点

Greater than 24°C

24°C 以上

Film thickness

涂装膜厚

Dry 40-80 microns/coat Wet : 83-167microns/coat

干膜: 40-80 微米/道 湿膜: 83-167 微米/道

Theoretical Coverage

理论涂覆率

0.215Kg/m²/80 microns

0.215 千克/平方米/80 微米

Practical coverage depending on surface conditions, environment, applications, etc.

实际涂覆率与表面处理, 外界环境, 施工方法等多种因素有关。

APPLICATION

施工

Application Temperature

施工温度

5°C-40°C

Mixing

混合

Combine Base with Hardener, mix thoroughly with power agitator

混合主剂与固化剂，使用动力工具搅拌均匀

Mixing Ratio

混合比例

Base/Hardener=5.5/1(by weight)

主剂/固化剂=5.5/1 (质量比)

Pot life	10°C	20°C	30°C
混合使用期	12hrs	8hrs	8hrs

Application Methods
施工方法

Airless spray, air spray and roller
无气喷涂、空气喷涂、滚涂

Airless spray 无气喷涂

Nozzle tip	喷嘴尺寸	0.33mm-0.43mm
Nozzle pressure	出口压力	≥10Mpa
Thinning ratio	稀释比率	0-5% by volume (体积比)

Roller 滚涂

Thinning ratio	稀释比率	5-10% by volume (体积比)
----------------	------	-----------------------

Thinner
稀释剂

Epomarine Thinner #20
环氧稀释剂#20

Drying time & Overcoating interval	Temperature	温度	10°C	20°C	30°C
干燥时间&涂装间隔	Surface dry	指触干燥	6hrs	4hrs	2hrs
	Touch dry	半硬干燥	30hrs	24hrs	16hrs
	Min. interval	最小涂装间隔	30hrs	24hrs	16hrs
	Max. interval	最大涂装间隔	7days	7days	7days

Applied substrate
适用底材

Bare steel
裸钢

Typical topcoat
适用上涂

EPOMARINE AE-10.
耐油防静电涂料

STORAGE
贮存

Store in dry, cool condition and away from sources of heat and ignition. Containers must be kept tightly closed.

贮存于干燥阴凉的环境中，远离热源及火源。包装桶必须保持封闭。

Shelf life
贮存期限

12 months from date of production (25°C)
自生产之日起 12 个月 (25°C)

DISCLAIMER
提请注意

The information given on this sheet is to the best of our knowledge and accurate at the time of issuing. Since conditions of use are beyond the manufacturer's control, information contained herein is without warranty, implied or otherwise, and the suitability of the material for the use contemplated is the sole responsibility of the buyer. The information contained on this data sheet is subject to modification at any time due to our policy of modification and product development. Please check this date sheet is current prior to using the product.

本说明书所提供信息均为目前我方所掌握最全面正确的资料,鉴于产品使用条件非我方所能控制,此中信息不含担保,即仅在选取产品上对买方负责。由于我公司产品及生产工艺的不断发展,本说明书的内容也会随时进行更改,此中所有信息均以我方确认为主。产品使用前,请确认所持说明书为最新版本。

www.kansai.com.cn

Issued Date 2011/6/27
发行日期 2011/6/27